

## CHEMICAL COMPOSITION OF STAINLESS STEEL

Stainless Steel is essentially a low carbon steel which contains chromium at 10% or more by weight. It is this addition of chromium that gives the steel its unique stainless corrosion resisting Properties. The corrosion resistance and other useful properties of the steel are enhanced by increased chromium content and the addition of other elements such as molybdenum, nickel and nitrogen

Chemical Composition of Stainless Steel											Nearest Equivalent Specification		
UNS NO.	EN	BS	AISI Grade	C Max	Mn Max	P Max	S Max	Si Max	Cr	Ni	Mo	Cu	I.S.

### Austenitic

S20100	-	-	201	0.15	5.5/7.5	0.06	0.03	1	16.0/18.0	3.5/5.5	-	-	-
S20200	-	-	202	0.15	7.5/10	0.06	0.03	1	17.0/19.0	4.0/6.0	-	-	-
S30100	-	301S21	301	0.15	2.0max	0.045	0.040	1.0	16.0/18.0	6.0/8.0	-	-	10Cr17Ni7
S30200	-	-	302	0.15	2.0	0.045	0.030	1.0	17.0/19.0	8.0/10.0	-	-	07Cr18Ni9
S30300	-	303S31	303	0.15	2.0	0.045	0.15 min	1.0	17.0/19.0	8.0/10.0	-	-	15Cr18Ni9
S30400	1.4301	-	304	0.08	2.0	0.045	0.030	1.0	18.0/20.0	8.0/10.0	-	-	04Cr18Ni10
S30403	1.4307	304S11	304L	0.030	2.0	0.045	0.030	1.0	18.0/20.0	8.0/12.0	-	-	02Cr18Ni11
S30453	1.4306	304S61	304LN	0.030	2.0	0.045	0.030	0.75	18.0/20.0	8.0/11.0	-	-	-
S30409	-	-	304H	0.05	2.0	0.045	0.03	1	18.0/20.0	8.5/9.5	-	-	-
S30900	-	309S16	309	0.20	2.0max	0.045	0.030	1.0	22.0/24.0	12.0/15.0	-	-	20Cr24Ni12
S30908	1.4833	-	309S	0.08	2.0	0.045	0.030	1.0	22.0/24.0	12.0/15.0	-	-	-
S31009	-	-	310H	0.25	2.0	0.045	0.030	1.50	24.0/26.0	19.0/22.0	-	-	10Cr25Ni12
S31008	1.4845	-	310S	0.08	2.0	0.045	0.030	1.50	24.0/26.0	19.0/22.0	-	-	-
S31600	-	316S31	316	0.08	2.0	0.045	0.030	1.0	16.0/18.0	10.0/14.0	2.0/3.0	-	04Cr17Ni12Mo2
S31603	1.4404	316S11	316L	0.030	2.0	0.045	0.030	1.0	16.0/18.0	10.0/14.0	2.0/3.0	-	03Cr17Ni12Mo2
S31653	-	316S61	316LN	0.030	2.0	0.045	0.030	0.75	16.0/18.0	10.0/14.0	2.0/3.0	-	-
S31635	1.4571	320S31	316Ti	0.080	2.0	0.045	0.030	1.0	16.0/18.0	10.0/14.0	2.0/3.0	-	-
S31700	-	-	317	0.08	2.0	0.045	0.030	1.0	18.0/20.0	11.0/15.0	3.0/4.0	-	-
S31703	-	317S12	317L	0.030	2.0	0.045	0.030	1.0	18.0/20.0	11.0/15.0	3.0/4.0	-	-
S31753	-	-	317LN	0.03	2.0	0.045	0.03	1	18.0/20.0	11.0/15.0	3.0/4.0	-	-
S32100	1.4541	321S31	321	0.08	2.0	0.045	0.030	1.0	17.0/19.0	9.0/12.0	-	-	04Cr18Ni10Ti20
S34700	-	347S31	347	0.08	2.0	0.045	0.030	1.0	17.0/19.0	9.0/12.0	-	-	04Cr18Ni10Nb-40
N08904	1.4539	-	904L	0.02	2.0	0.045	0.035	1	19.0/23.0	23.0/28.0	4.0-5.0	-	-

### Ferritic

S41000	-	410S21	410	0.15	1.00	0.040	0.030	1.0	11.50-13.50	0.75	...	...	...
S41008	1.4000	403S17	410S	0.08	1.00	0.040	0.030	1.0	11.50-13.50	0.60	...	...	...
S42900	-	-	429 <sup>s</sup>	0.12	1.00	0.040	0.030	1.0	14.00-16.00	...	...	...	...
S43000	1.4016	430S17	430	0.12	1.00	0.040	0.030	1.0	16.00-18.00	0.75	...	...	...
S43035	-	-	439	0.07	1.00	0.040	0.030	1.0	17.00-19.00	0.050	...	0.04	...
S44400	-	-	444	0.025	1.00	0.040	0.030	1.0	17.5-19.5	1.00	1.75-2.50	0.035	...
			446	0.20	1.50	0.040	0.030	0.50	11.40 / 13.00	-			
	-	-	409L	≤ 0.030	≤ 1.00	≤ 1.00	-	-	-	10.50~11.75	~	-	-

### Duplex & Super Duplex

S31803	1.4462	-	---	0.030	2.00	0.030	0.020	1.0	21.0-23.0	4.5-6.5	2.5-3.5	—	0.08-0.20
S32550	-	-	255 <sup>o</sup>	0.040	1.50	0.040	0.030	1.0	24.0-27.0	4.5-6.5	2.9-3.9	1.50-2.50	0.10-0.25
S32750	1.441	-	2507	0.030	1.20	0.035	0.020	0.8	24.0-26.0	6.0-8.0	3.0-5.0	0.50	0.24-0.32
S32760	-	-	---	0.030	1.00	0.030	0.010	1.0	24.0-26.0	6.0-8.0	3.0-4.0	0.50-1.00	0.20-0.30